

**PRODUCTION OF CELLULOSE ACETATE FROM
Acacia mangium FOR WOOD COATING LACQUER**

MELISSA SHARMAH BTE GILBERT @ JESUET

**THESIS SUBMITTED IN PARTIAL FULFILLMENT
FOR THE DEGREE OF MASTER OF SCIENCE**

**PERPUSTAKAAN
UNIVERSITI MALAYSIA SABAH**

**FACULTY OF SCIENCE AND NATURAL RESOURCES
UNIVERSITI MALAYSIA SABAH**

2016

UNIVERSITI MALAYSIA SABAH

BORANG PENGESAHAN STATUS TESIS

JUDUL: PRODUCTION OF CELLULOSE ACETATE FROM *Acacia mangium*
FOR WOOD COATING LACQUER
IJAZAH: SARJANA SAINS

Saya MELISSA SHARMAH BTE GILBERT @ JESUET, Sesi Pengajian 2011-2016, mengaku membenarkan tesis Sarjana ini disimpan di Perpustakaan Universiti Malaysia Sabah dengan syarat-syarat kegunaan seperti berikut:-

1. Tesis ini adalah hak milik Universiti Malaysia Sabah.
2. Perpustakaan Universiti Malaysia Sabah dibenarkan membuat salinan untuk tujuan pengajian sahaja.
3. Perpustakaan dibenarkan membuat salinan tesis ini sebagai bahan pertukaran antara institusi pengajian tinggi.
4. Sila tandakan (/).

☐

SULIT

(Mengandungi maklumat yang berdarjah keselamatan atau kepentingan Malaysia seperti yang termaktub di dalam AKTA RAHSIA RASMI 1972)

☐

TERHAD

(Mengandungi maklumat TERHAD yang telah ditentukan oleh organisasi/badan di mana penyelidikan dijalankan)

☒

TIDAK TERHAD

Disahkan oleh,

NURULAIN BINTI ISMAIL
LIBRARIAN

UNIVERSITI MALAYSIA SABAH


(Tandatangan Pustakawan)


(Tandatangan Penulis)

Alamat Tetap: Peti Surat 13922,
88845 Kota Kinabalu.

Tarikh: 26 Januari 2016


(ISMAWATI PALLE)

Penyelia


(DR. LIEW KANG CHIANG)
Penyelia Bersama




UMS
UNIVERSITI MALAYSIA SABAH

DECLARATION

I hereby declare that this submission is my own work and that, to the best of my knowledge and beliefs, contains no material previously publishes or written by another person nor material except where due acknowledgement has been made by text.

26th January 2016



Melissa Sharmah Bte Gilbert @ Jesuet
PF20118121

PERUSTAKAAN
UNIVERSITI MALAYSIA SABAH



CERTIFICATION

NAME : MELISSA SHARMAH BTE GILBERT @ JESUET
MATRIC NO. : PF20118121
TITLE : PRODUCTION OF CELLULOSE ACETATE FROM *Acacia mangium* FOR WOOD COATING LACQUER
DEGREE : MASTER OF SCIENCE (FORESTRY)
VIVA DATE : 9th DECEMBER 2015

CERTIFIED BY

1. SUPERVISOR

Ismawati Palle

Signature



2. CO-SUPERVISOR

Assoc. Prof. Dr. Liew Kang Chiang



CERTIFICATION

NAME : MELISSA SHARMAH BTE GILBERT @ JESUET
MATRIC NO. : PF20118121
TITLE : PRODUCTION OF CELLULOSE ACETATE FROM *Acacia mangium* FOR WOOD COATING LACQUER
DEGREE : MASTER OF SCIENCE (FORESTRY)
VIVA DATE : 9th DECEMBER 2015

CERTIFIED BY

1. SUPERVISOR

Ismawati Palle

Signature

2. CO-SUPERVISOR

Assoc. Prof. Dr. Liew Kang Chiang

ACKNOWLEDGEMENTS

I would like to take this opportunity to express my sincere appreciation and heartfelt gratitude to the following, who shared their knowledge, expertise, encouragements, and cooperation, by guiding me through this hardship that I have gotten myself voluntarily partaking to, with a couple of nudges from dad, in which people would call it in high admiration and dissolute indifference, Master's degree.

I would like to acknowledge our School of International Tropical Forestry (SITF), in which is now known as the Faculty of Science and Natural Resources (Forestry Complex), Universiti Malaysia Sabah, who inexhaustibly provided me with a shed (and air conditioners) to fight off the heat from the tiresome weathers, chemicals that burns through shoes, the knight-in-shining manpower, as well as materials to dwell with in conducting this research project. A shout out to my thesis supervisor, Miss Ismawati Palle, who had unknowingly agreed on supervising a monstrosity of a person that is I, to the end of my master's. Your kindness and affliction will forever haunt my dreams, just like your 5 a.m. text messages. To Dr. Liew Kang Chiang, my constant tormentor but in a fatherly sort of way co-supervisor, thank you for always keeping me sharp and on my feet with your quizzing eyebrows.

The deepest sense of gratitude especially to my mother and father, Mrs. Masneh Jain and Mr. Gilbert Laimon, for all the morale and financial support to the daughter that you made further her studies unwillingly. Best mandatory order ever. Thank you to my three favorite laboratory assistant, Mr. Azli Sulid, Mr. Abdul Airin, and Mr. Mohd. Rizan, for their aid in handling machines and apparatus, as well as knowledge and advices, for this project. To my fellow comrades, Elizabeth James, Julia Ak Nelson, Sitti Suraidah Anas, Hue Su Wah, Ellyza Syazzana, Dr. Benny Yeong, and many more, thank you and I wish you all the worst in enduring the torture.

I would also like to express my overall heartfelt gratitude to the rest of my family and friends for the never-ending support especially in the physical/mental contribution. Without you guys, I would never have made it, or even if I did made it, I would have been bald and super conceited. Thank you for not making me bald, especially, and gripped my legs so that I would not fly to the sun. Lastly, I would also like to thank those unnamed contributors in their cooperation and participation, directly and indirectly, in successfully helping me finish my upward climb to my (academic) K2 Mountain.

CONFIDENTIAL

v

ABSTRAK

PENGHASILAN SELULOSA ASETAT DARI PULPA *Acacia mangium* UNTUK LAKUER PENYALUT KAYU

Selulosa asetat (CA) adalah fiber industri separa sintetik yang mempunyai aplikasi yang luas termasuk bahan untuk acuan produk dan tekstil, selain daripada membran turas, puntung rokok, dan penyalut. Kajian ini memberi tumpuan terhadap penghasilan penyalut daripada CA yang diperbuat daripada Acacia mangium. Ia merangkumi pemilihan serat A. mangium untuk fabrikasi pengantara CA, diikuti dengan keadaan yang optimum untuk penghasilan CA, dan akhirnya prestasi produk akhir CA berasaskan A. mangium bagi penyalut kayu. Ciri-ciri fiber kayu dan pulpa dari A. mangium telah ditentukan dan dibandingkan, yang mana fiber pulpa menunjukkan potensi yang lebih baik dalam penghasilan CA kerana komposisi selulosa yang tinggi iaitu melebihi 100% perbezaan jika dibandingkan dengan fiber kayu. Dari segi struktur, pulpa mempunyai struktur fibril yang lebih baik dan nilai yang lebih tinggi berbanding serat kayu untuk dimensi serat, dengan peratusan perbezaan tidak melebihi 10% bagi hampir semua nilai. Fiber pulpa yang telah dipilih seterusnya melalui proses asetilasi, melalui tindakbalas dengan asetik anhidrida dan asid asetik dimana beberapa keadaan telah dimanipulasi, termasuk proses pra-rawatan, jumlah pemangkin, saiz partikel pulpa, dan masa tindakbalas untuk memperolehi keadaan optimum. Keputusan menunjukkan pra-rawatan fiber pulpa A. mangium dengan saiz jaringan partikel 200 yang bertindakbalas selama 36 jam dengan penggunaan pemangkin tertinggi berjumlah 0.10 ml telah memperolehi nilai tahap penggantian (DS) yang paling ideal untuk pembentukan penyalut, iaitu 2.81. Manakala, pembentukan penyalut lakuer asetat seterusnya telah mengikuti paten A.S. bernombor 2426379 yang melibatkan percampuran melamin formaldehid dan juga etil asetat. Prestasi lakuer A. mangium selulosa asetat (AMCA) telah dinilai dan dibandingkan dengan lakuer kawalan yang diperbuat daripada CA komersil (CCA), berdasarkan dengan prestasi mekanikal dan fizikal. Prestasi lakuer AMCA terbukti setanding atau lebih baik daripada CCA lakuer dengan daya rintangan yang lebih baik terhadap kesan kotor serta kadar penyerapan air yang rendah untuk ciri fizikal, dan ketahanan yang tinggi untuk ujian impak, kekerasan, dan lelasan untuk prestasi mekanikal. Dapatan kajian perkembangan lakuer asetat ini mengukuhkan lagi kebolegunaan sebatian organik terbanyak di muka bumi ini iaitu selulosa sebagai alternatif kepada produk berasaskan petroleum, selain menunjukkan kesesuaian bahan mentah ini untuk perkembangan produk bukan konvensional bagi spesies A. mangium.

TABLE OF CONTENTS

TITLE	Page i
DECLARATION	ii
CONFIRMATION	iii
ACKNOWLEDGEMENT	iv
ABSTRACT	v
ABSTRAK	vi
TABLE OF CONTENTS	vii
LIST OF TABLES	x
LIST OF FIGURES	xi
LIST OF ABBREVIATIONS	xiii
LIST OF FORMULAS	xiv
LIST OF SYMBOLS	xv
CHAPTER 1: INTRODUCTION	
1.1 Background of Study	1
1.2 Problem Statement and Justification	3
1.3 Objectives	5
CHAPTER 2: LITERATURE REVIEW	
2.1 <i>Acacia mangium</i>	6
2.1.1 Utilization	8
2.1.2 Chemical Composition	10
2.2 Chemical Characteristic	11
2.2.1 Cellulose	11
2.2.2 Hemicellulose	12
2.2.3 Lignin	14
2.2.4 Extractives	15
2.3 Cellulose Derivatives	16
2.3.1 Cellulose Ethers	16
2.3.2 Cellulose Esters	17
2.4 Cellulose Acetate	17
2.4.1 Production of Cellulose Acetate	19
2.4.2 Utilization	22
2.5 Lacquer	24
2.5.1 Production of Acetate Lacquer	25
CHAPTER 3: CHEMICAL CONSTITUENT AND FIBER DIMENSIONS OF <i>Acacia mangium</i>	
3.1 Introduction	26
3.2 Materials	28
3.3 Determination of Chemical Composition of <i>Acacia mangium</i>	28



3.3.1	Extractives	30
3.3.2	Holocellulose extraction	30
3.3.3	Cellulose extraction	31
3.3.4	Lignin extraction	32
3.4	Determination of Fiber Dimension of <i>Acacia mangium</i>	33
3.5	Results and Discussion	34
3.5.1	Chemical composition of <i>Acacia mangium</i>	34
3.5.2	Fiber Dimension of <i>Acacia mangium</i>	38
3.5	Conclusion	42

CHAPTER 4: CELLULOSE ACETATE PRODUCTION FROM *Acacia mangium* PULP

4.1	Introduction	43
4.2	Materials	45
4.3	Cellulose Acetate Synthesis	45
4.3.1	Pretreatment	45
4.3.2	Acetylation	46
4.3.3	Hydrolysis	47
4.3.4	Extraction	48
4.4	Evaluation of Cellulose Acetate Properties	49
4.4.1	Degree of Substitution	49
4.4.2	Rate of Efficiency	50
4.4.3	Weight Percentage Gained	51
4.4.4	Fourier Transform Infrared (FTIR) Spectroscopy	52
4.5	Results and Discussion	53
4.5.1	Effects of Pretreatment	53
4.5.2	Effect of Particle Mesh Size	55
4.5.3	Effects of Catalyst	57
4.5.4	Effects of Reaction Time	59
4.5.5	Identification and Characterization of Infrared Spectroscopy	62
4.6	Conclusion	66

CHAPTER 5: ACETATE LACQUER PRODUCTION

5.1	Introduction	67
5.2	Materials	68
5.3	Acetate Lacquer Production and Properties	68
5.3.1	Formation of Lacquer	68
5.3.2	Evaluation of Basic Lacquer Properties	70
5.3.3	Evaluation of Applied Lacquer Performance	73
5.4	Results and Discussion	81
5.4.1	Basic Properties	81
5.4.2	Mechanical Performance	84
5.4.3	Physical Performance	90
5.5	Conclusion	98

CHAPTER 6: OVERALL DISCUSSION

6.1	Chemical Constituent and Fiber Dimensions of <i>Acacia mangium</i>	99
6.2	Cellulose Acetate Production from <i>Acacia mangium</i> Pulp	101
6.3	Acetate Lacquer Production	103

CHAPTER 7: CONCLUSIONS AND RECOMMENDATIONS

7.1	Conclusions	106
7.2	Recommendations	107

REFERENCES	108
APPENDIX A	122
APPENDIX B	123
APPENDIX C	124
APPENDIX D	125

LIST OF TABLES

	Page
Table 2.1	8
Table 2.2	11
Table 3.1	35
Table 3.2	40
Table 5.1	75
Table 5.2	82
Table 5.3	85
Table 5.4	91

LIST OF FIGURES

	Page
Figure 2.1	7
Figure 2.2	9
Figure 2.3	10
Figure 2.4	12
Figure 2.5	13
Figure 2.6	15
Figure 2.7	17
Figure 2.8	18
Figure 2.9	19
Figure 2.10	21
Figure 2.11	23
Figure 2.12	24
Figure 3.1	29
Figure 3.2	39
Figure 3.3	39
Figure 4.1	46
Figure 4.2	47
Figure 4.3	48
Figure 4.4	49
Figure 4.5	54
Figure 4.6	55
Figure 4.7	56
Figure 4.8	57
Figure 4.9	58
Figure 4.10	59
Figure 4.11	60
Figure 4.12	61
Figure 4.13	64
Figure 4.14	65
Figure 5.1	69
Figure 5.2	71
Figure 5.3	71
Figure 5.4	72

Figure5.5	Dust-free method to determine the drying time	73
Figure 5.6	Film thickness via microscope observation	74
Figure5.7	Impact test on coated <i>Acacia mangium</i> block by impact ball	75
Figure5.8	Bending test on lacquer-applied block	76
Figure5.9	Principle of classifying paint film adhesion in the cross-cut test	77
Figure5.10	The pencil was hold in a 45° angle to test the hardness of the coat	78
Figure5.11	Chemical and staining test	79
Figure5.12	Water absorption test	81
Figure5.13	One circular indentation appeared on the (a) AMCA lacquer while three or more circular indentation and cracking appeared on the (b) CCA lacquer during impact test	86
Figure 5.14	Flaking percentage of approximately 15 % for the (a) AMCA lacquer and 5 % for the (b) CCA lacquer after adhesion test	88
Figure 5.15	Abrasion resistance on the (a) AMCA lacquer with 288 cycles and (b) CCA lacquer with 271 cycles	89
Figure 5.16	Plastic deformation appeared on the (a) AMCA and (b) CCA lacquer after being tested with a 3H and 2H grade pencil respectively	90
Figure 5.17	Damages of CCA lacquer coating in terms of surface cracking by (a) hydrochloric acid and (b) sulfuric acid, and surface clouding by (c) acetic acid and (d) acetone	92
Figure 5.18	Damages of AMCA lacquer coating in terms of surface cracking by (a) hydrochloric acid and (b) sulfuric acid, and surface clouding by (c) acetic acid, (d) acetone, (e) dichloromethane, and (f) sodium hydroxide	93
Figure 5.19	Stains on the CCA lacquer coating by (a) lip tint (b) coffee, (c) carbonated drink, (d) tea, and (e) oil	95
Figure 5.20	Stains on the AMCA lacquer coating by (a) lip tint (b) coffee, and (c) tea	95
Figure 5.21	Early signs of defects such as (a) perspiration and other defects (b) blister, (c) crater, and (d) shrinkage appeared due to the changing temperatures and humidity	97

LIST OF ABBREVIATIONS

AMCA	<i>Acacia mangium</i> cellulose acetate
ASH	Action on smoking and health
CA	Cellulose acetate
CCA	Commercial cellulose acetate
CMC	Carboxymethyl cellulose
DBH	Diameter breast height
DP	Degree of polymerization
DS	Degree of substitution
EIA	Ethiopian embassy
GAMA	Global Acetate Manufacturers Association
LCD	Liquid crystal display
MDF	Medium density fiberboard
MOE	Modulus of elasticity
MOR	Modulus of rupture
RE	Rate of efficiency
TAPPI	Technical Association of the Pulp and Paper Industry
WPG	Weight percentage gained

LIST OF EQUATIONS

		Page
Equation 3.1	Moisture content	30
Equation 3.2	Extractive content	30
Equation 3.3	Holocellulose content	31
Equation 3.4	Cellulose content	32
Equation 3.5	Lignin content	32
Equation 3.6	Slenderness ratio	34
Equation 3.7	Runkel ratio	34
Equation 3.8	Coefficient of suppleness	34
Equation 3.9	Flexibility coefficient	34
Equation 4.1	Degree of substitution	50
Equation 4.2	Rate of efficiency	51
Equation 4.3	Weight percentage gained	52
Equation 5.1	Water absorption rate	80

LIST OF SYMBOLS

\pm	Plus minus
μm	Micrometre

CHAPTER 1

INTRODUCTION

1.1 Background of Study

Plants play a constitutive role in the functioning of the ecosystem. Apart from conducting a colossal part in the carbon cycle, plants are also one of the main contributors to the most abundant organic compound on Earth, the cellulose. According to Varshney and Naithani (2011), there are about 10^{11} to 10^{12} tons of cellulose synthesized annually through photosynthesis, as cellulose is one of the main components in plants besides hemicellulose and lignin, comprising approximately 45 to 50% of all carbon in vegetation (Haygreen and Bowyer, 1989). Usually being extracted through processes such as pulping or cellulose purification, cellulose is extensively used as raw materials in paper production (Villar, Revilla, Gomez, Carbajo and Simon, 2009) and lignocellulosic bioethanol production (Limayem and Ricke, 2012).

The unique structure of cellulose enables it to be one of the more easily modified elements, as it is constituted of long chains of glycosidic units with unlimited hydroxyl groups. With the promise of a never-ending supply and high modification potential, cellulose has a high potential in the development of bio-based material engineering such as one of the promising but far long ago established, cellulose derivatives. Derivatives by definition are imitative materials, which is based from a natural element or source such as cellulose, where the properties are profoundly improved from its original form through the process of chemical alterations. As for cellulose derivatives, it includes processes such as etherification and esterification to obtain the targeted trait or characteristics in forming a new and improved product, which individually incorporates chemical reactions with alkaline and acidic reagents, respectively. Among the cellulose derivatives available includes carboxymethyl cellulose (CMC) and ethyl cellulose for ethers, and cellulose acetate for esters (Granström, 2009).

For this study, cellulose acetate was produced from *Acacia mangium* for the production of acetate lacquer. Cellulose Acetate (CA) is one of the cellulose derivatives, specifically ester, which is produced through the substitution of hydroxyl group by acetyl groups provided from acetic acids. The procedures in fabricating the CA are slightly modified following previous studies to obtain the optimum condition and providing lower cost alternative procedures that includes different types of pretreatments, reaction time, catalyst, and mesh size. Meanwhile the selection of *A. mangium* is based on Pinto, Evtuguin, and Neto (2005), where it shows an impressive composition of cellulose with an overall composition of over 45% in dry weight, hence is chosen to be the main source of cellulose for the project as an alternative of the cellulose-filled cotton.

According to Saka (2004), there are a number of other selections for the source of cellulose, which typically includes cotton and wood pulps. The production of CA can be derived from most plants, but is highly recommended for plants with a high composition of α -cellulose. There has been a number of previous researches done on the production of cellulose acetate from a wide range of plant species, such as agricultural biomass that includes sugarcane bagasse (Shaikh, Pandare, Nair, and Varma, 2009), corn fiber, rice hulls and wheat straw (Biswas, Saha, Lawton, Shogren, and Willett, 2006) and cotton byproducts (Cheng, Dowd, Selling, and Biswas, 2010), as well as hard and soft wood. Mainly the wood species suitability for the derivation of cellulose refers similarly to the production of pulp for paper itself, similarly following the suitable species such as birch and spruce for softwood (Laine, 2005) as well as Yemane (Palaypayon and Batalon, 2002) and Batai (Bunye, 1990) for tropical hardwoods.

Due to the production of CA from biodegradable materials, it is one of the long lasting derivatives with numerous developments since more than a century ago. There are four (4) main categories of CA products, which include fibers for textile application, tough and moldable materials for plastics, film for tapes and coatings, and as effective filter for beverages and cigarette filters (Rustemeyer, 2004). Properties such as hypoallergenic, high water absorption, and mold/mildew resistant are among the excellent qualities of CA for the utilization as a raw

material for the textile industry. Meanwhile, properties such as thermoplasticity, highly soluble in solvents, and bondable in plasticizers, makes it a suitable substance for the film and membrane industry, with an additional biodegradability trait due to the development from natural renewable resources (Fischer, Thummler, Volkert, Hettrich, Schmidt, and Fischer, 2008).

One of the oldest products for CA is lacquer, which used to be called dope during World War I. Acetate lacquer is a type of glossy clear coating that forms a film on the surface of the area through the evaporation of the solvents, differentiating itself from naturally derived resin-based lacquers. The film formation mechanism differs from the resin-based lacquers due its dependability towards solvent, where crosslinking among monomers happens with the evaporation of solvents. It is highly used in the finishing act in the wood industry as a barrier from the exposure of weather and pests, and considered as a beautifier of the products. Lacquer produced from CA namely will adapt the better qualities of the CA itself such as the hypoallergenic and resistance to molds, and proven to be of an advantage even more than other cellulose esters such as Nitrocellulose that was usually used to produce nitrate films, but due to its flammability, was developed into gun powders instead (Gettens and Stout, 2012).

1.2 Problem Statement and Justification

The extricable resources of the Earth are reckonable, in spite of the disputes over its depletion rate, especially to the non-renewable resources such as petroleum. Based on the Peak theory by Marion King Hubbert, the rate of petroleum production of the reserve over time would resemble a bell curve for any given geographical area, in which anticipates an exponential growth, followed by an overall peak petroleum production before encountering a decline of oil capacity right after. The said theory successfully predicted the peak oil production for the 48 states of the United States of America, which peaked in 1970, within the estimated 1966 – 1972 augured year (Towler, 2014).

With the act of depleting resources became fully aware, the demands for bio-based products; be it chemicals, materials, and energy are envisioned to be

fully in amplified demands, hence, rigorously metamorphose the material industries, notably in the petroleum alternatives industry such as plastics and biofuels, stemming from the proposition of sustainability and green energy. Developments in alternative productions such as soy-based biodiesels (Tomei and Upham, 2009) and plasticizers (Galli, Nucci, Pirola, and Bianchi, 2014) have garnered attention in the chemical engineering world due to its perceptible improvements to the environmental impact and workers' safety.

Likewise, the consumers of the world are also becoming more aware in the advantages in using biodegradable products or machines that emit lower carbon dioxide emission or high carbon sinkage. Alternatives to coating products with paraffin wax, which is a petroleum-based derivative, are expected to be in high demands such as the starch-based (Rohula, Kawiji, Andre, and Andik, 2013) and lignin-based (Narapakdeesakul, Sridach, and Wittaya, 2013) coatings. With a higher demand for alternatives, succeeding action will also increase the demands of renewable resources, subsequently increasing the supply for these bio-based materials resources such as trees and other vegetation.

As in Malaysia, we are naturally blessed with a rich condition that is most suitable in deciduous as well as some of the coniferous trees, in other words, sustainably rich in resources. Exploiting the perfect condition for timber plantations, production of fast-growing woods with inferior quality has resulted to some unwanted implications in utilization of it as solid wood. With the intention of developing the usability of plantation timbers that has an unfortunately low desirability factor, it is more feasible and cost effective for its development in the cellulose-based application and industrialization (Varmola, 2002).

In Sabah alone, *Acacia mangium* has been steadily producing logs for industrial use since the early 1990s. With more than 4 000 000 m³ of plantation log production in 2011, *A. mangium* is one of the major contributor in the Sabah timber supply with a fourth of the count, consequently providing a promising supply of cellulose (Sabah Forestry Department, 2012). With only an approximately 3% of the overall production exported, the majority of the *A. mangium* usage are

used as materials for the downstream processing in Sabah, hence a number of potential of the fast growing timber as raw material for other fiber or cellulose products has also been carried out such as for acetylated Medium Density Fiberboards (Unchi, 1996), pulp for papermaking (Lee, 2004) and particleboards (Sarmin, Zakaria, Kasim, and Shafie, 2013). Apart from the Thus, this study will be focusing on improving the potential application of timber as fiber or cellulose based, specifically the feasibility of *Acacia mangium* to be developed into a bio-based ester material, specifically cellulose acetate (CA) in being consequently developed into wood coating lacquer.

1.3 Objectives

The focus of this study was to produce cellulose acetate from *Acacia mangium* pulp, and then subsequently develop it into wood laminating lacquer. It follows four objectives, which includes;

1. To determine and compare the chemical composition and fiber dimensions between the *Acacia mangium* pulp and wood fiber.
2. To evaluate the effect of the manipulated condition towards the degree of substitution, weight percentage gained, and rate of efficiency in the production of cellulose acetate from *Acacia mangium*.
3. To identify and characterize the spectroscopy of the cellulose acetate produced.
4. To evaluate and compare the properties of the basic and applied lacquer between the *Acacia mangium* acetate lacquer and a commercial cellulose acetate lacquer.

CHAPTER 2

LITERATURE REVIEW

2.1 *Acacia mangium*

Acacia mangium (Figure 2.1) is a leguminous tree species from the family of Fabaceae. Native of Australia, Indonesia and Papua New Guinea, which is also widely grown exotically in countries such as Malaysia, South Africa and Vietnam. *A. mangium* is originally planted in the Malesian region such as Thailand and Papua New Guinea as an ornamental, however due to its fast growing and utilization potential properties, significant areas of plantations have been established in numerous countries such as India, Indonesia and Malaysia (Hegde, Palanisamy, and Jae, 2013). In Sabah alone, the FSC certified forest plantation, which includes SAFODA and Sabah Softwood Bhd., covers up more than 40 000 hectares that is dominantly populated by *Acacia mangium* (Sabah Forestry Department, 2012).

Being a single-stemmed evergreen tree, *A. mangium* can grow up to 25-35 m in height with a straight bole, reaches roughly up to six (6) meters increment in height and 15 cm in diameter breast height (DBH) per year. The bark surface is rough, rutted longitudinally and differs in colors, from the range of pale grey-brown to brown, while the sapwood and heartwood may have distinct color from each other. The former is often white or yellowish white and the latter is yellowish brown to golden-brown when fresh, but oxidized to dull brown when exposed longer. It is a light hardwood that has the density ranges from 400-480 kg/m³ (Sahri, Ibrahim, and AbShukor, 1993), giving it good reputation as a fast growing timber species with considerably good form and utilization potential.



Figure 2.1: *Acacia mangium* tree sapling.

Acacia mangium is a durable tree species that can endure extreme conditions such as the wide variety of soil types, low soil fertility and acidic pH soil as low as 3.8. It can also tolerate extreme weather such as heavy rainfall and drought, with significant difference in growth rate. This species was also successfully planted on areas of shifting cultivation colonized by *Imperata cylindrica* grass such as in Indonesia (Otsamo, 2001). Apart from its tolerability, the utilization of the species as timber is also favorable, as it can be easily sawn, drilled, polished and turned. The dimensional stability is within a satisfactory range state, with green to air-dried shrinkage of 6.4% in the tangential section and 2.7% in radials (Kader and Sahri, 1992). *A. mangium* has one of the highest moisture content in assorted age groups, in the heartwood more than sapwood with the highest reaching up to 253% and 149% respectively (Lim, Gan, and Choo, 2003), substantially increasing its MOR and MOE in its dried state (Table 2.1).

REFERENCES

- Ambjörnsson, H. A., Schenzel, K., & Germgard, U. 2013. Carboxymethyl cellulose produced at different mercerization conditions and characterized by NIR FT Raman Spectroscopy in combination with multivariate analytical methods. *BioResources*. **8** (2): 1918-1932.
- AnttiOtsamo. 2001. *Forest Plantations on Imperata grasslands in Indonesia-Establishment, Silviculture, and Utilization Potential*. Finland: University of Helsinki.
- ASH. 2009. *What's in a cigarette?* United Kingdom: Action on Smoking and Health Fact Sheet.
- ASTM. 2005. *D3363 Standard test methods for film hardness by pencil test*. United States: ASTM International.
- ASTM. 2009. *D1640 Standard test methods for drying, curing, or film formation of organic coatings at room temperature*. West Conchochocken, PA: ASTM International.
- ASTM. 2015. *D870 Practice for Testing Water Resistance of Coatings Using water Immersion*. United States: ASTM International.
- Badger, P. C. 2002. Ethanol from cellulose: A general review. In Janick, J. & Whipkey, A. (eds.). *Trends in new crops and new uses*, pp. 17-21. Alexandria, VA: ASHS Press.
- Bektas, I., Tutus, A., & Eroglu, H. 1999. A study of the suitability of Calabrian pine (*Pinus burtia*, Jen) for pulp and paper manufacture. *Turkish Journal of Agriculture and Forestry*. **23** (3): 589-597.
- Bhatt, B. I. & Vora, S. M. 2004. *Stoichiometry*. 4th ed. New Delhi: Tata McGraw-Hill Education.
- Bianchini, J. & Antonio, R. 2003. The Effect of Particle Size on the Leaching of *Scirpus cubensis* POEPP and KUNTH. *Brazilian Journal of Biology*. **63** (2): 195-205.
- Biswas, A., Saha, B. C., Lawton, J. W., Shogren, R. L., & Willett, J. L. (2006). Process for Obtaining Cellulose Acetate from Agricultural By-products. *Carbohydrate Polymers*. **64** (1): 134-137.

- Biswas, A., Selling, G. S., Shogren, R. L., Willett, J. L., Buchanan, C. M., & Cheng, H. N. 2009. Iodine-catalyzed esterification of polysaccharides. *Chemistry Today*. **27** (4), 4–6.
- Boreskov, G. K. 2003. *Heterogeneous catalysis*. Hauppauge, N. Y.: Nova Science Publishers.
- Brindha, D., Vinodhini, S., & Alarmelumangai, K. 2012. Fiber Dimension and Chemical Contents of Fiber from *Passiflora Foetida*, L. and Their Suitability in Paper Production. *Science Research Reporter*. **2** (3): 210-219.
- British Standard. 1980. *3692 (6) Impact test*. . British Standard Institute.
- Campbell, M. M. & Sederoff, R. R. 1996. Variation in lignin content and composition. *Plant Physiology*. **110** (1): 3-13.
- Cao, N., Oden, K., & Glasser, W. G. 2013. *U.S. Patent WO2013170238*. Washington, DC: USA.
- Carollo, P. & Grospietro, B. 2004. Plastic materials. *Macromolecular symposia*. Wiley-VCH.
- Carvalho, F., Duarte, L. C., & Gírio, F. M. 2008. Hemicellulose Refineries: A Review on Biomass Pretreatments. *Journal of Scientific and Industrial Research*. **67**: 849-864.
- Cerqueira, D. A., Filho, G. R., Assuncao, D. S., Meireles, C. D. S., Toledo, L. C., Zeni, M., Mello, K., & Duarte, J. 2008. Characterization of Cellulose Triacetate Membranes Produced from Sugarcane Bagasse Using PEG 600 as Additive. *Polymer Bulletin*. **60** (2-3): 397-404.
- Cerquiera, D. A., Filho, G. R., & Meireles, C. S. 2007. Optimization of sugarcane bagasse cellulose acetylation. *Carbohydrate Polymer*. **69** (3): 579-582.
- Cheng, H. N., Dowd, M. K., Selling, G. W., & Biswas, A. 2010. Synthesis of Cellulose Acetate from Cotton Byproducts. *Carbohydrate Polymers*. **80** (2): 449-452.
- Christiane Laine. 2005. *Structures of hemicelluloses and pectins in wood and pulp*. Finland: Helsinki University of Technology.
- Dantas, P. A. & Botaro, V. R. 2012. Synthesis and Characterization of a New Cellulose Acetate-Propionate Gel: Crosslinking Density Determination. *Open Journal of Polymer Chemistry*. **2** (4): 144-151.
- Davis, J. 2000. *Lacquers for Wood- Then and Now*. US: MACLAC.

- Dawson, L. &Boopathy, R. 2008. Cellulosic Ethanol Production from Sugarcane Bagasse without Enzymatic Saccharification. *Bioresources*.**3** (2): 452-460.
- Dhani Raj Bogati. 2011. *Cellulose based biochemical and their applications*. Finland: Saimaa University of Applied Sciences.
- Dilik, T., Erdinler, S., Hazir, E., Koc, H., &Hiziroglu, S. 2015. Adhesion strength of wood based composites coated with cellulosic and polyurethane paints. *Advances in Materials Science and Engineering*.**2015** (5): 1-5.
- Dill, D. 2006a. *Acid-base equilibria*. USA: Boston University.
- Dill, D. 2006b. *General chemistry*. USA: Boston University.
- Dombro, D. B. 2009. *Acacia mangium*: Amazonian Reforestation's miracle tree.
- Dutta, S., De, S., Saha, B., &Alam, M. I. 2012. Advances in conversion of hemicellulosic biomass to furfural and upgrading to biofuels. *Catalysis Science and Technology*. **2** (10): 2025-2036.
- Eastman. Eastman Chromspun™ acetate yarn. Retrieved from <http://www.eastman.com/Products/Pages/ProductHome.aspx?Product=71056296>. 27 Dec. 2015.
- EIA. 2010. *Profile on the production of cellulose acetate*. United Kingdom, London: Ethiopian Investman Agency.
- Fauzi, M. D., Mohammad, A., MohamadNasir, M. I., & Wan Rosli, W. D. 2014. Synthesis and characterization of cellulose acetate from TCF oil palm empty fruit bunch pulp. *BioResources*. **9** (3): 4710-4721.
- Feller, R. L. & Wilt, W. 1990. *Evaluation of cellulose ethers for conservation*. The Getty Conservation Institute.
- Fetch Eyewear. No yr Retrieved from <https://www.fetcheyewear.com/gallery/women/designer-reading-glasses>. 27 Dec. 2015.
- Filho, G. R., Monteiro, D. S., Meireles, C. D. S., Assuncao, R. M. N. D., Cerqueira, D. A., Barud, H. S., Ribeiro, S. J. L., &Messadeq, Y. 2008. Synthesis and characterization of Cellulose Acetate Produced from Recycled Newspaper. *Carbohydrate Polymers*. **73** (1): 74-82.
- Filho, G. R., Silva, R. C., Meireles, S., Assuncao, R. M. N., &Otaguro, H. 2005. Water flux through blends from waste materials: Cellulose acetate (from

sugar can bagasse) with polystyrene (from plastic cups). *Journal of Applied Polymer Science*.**96** (2): 516-522.

- Fischer, S., Thummler, K., Volkert, B., Hettrich, K., Schmidt, I., & Fischer, K. 2008. Properties and applications of cellulose acetate. In Heinze, T., Janura, M., & Koschella, A. *Structure and Properties of Cellulose. Macromolecular symposia*. **262** (1): 89-96. Weinheim: Wiley-VCH.
- Ford, B. B. 1991. *Lacquer and lacquering*. New York: Metropolitan Museum of Art.
- Franklin, G. L. 1954. A Rapid Method for Softening Wood for Anatomical Analysis. *Tropical Woods Technical Journal*.**88**(3): 35-36
- Froschauer, c., Hummel, M., Iakovlev, M., Roselli, A., Schottenberger, H., & Sixta, H. 2013. Separation of Hemicellulose and Cellulose from Wood Pulp by Means of Ionic Liquid/Co-Solvent Systems. *Biomacromolecules*. **14** (6): 1741-1750.
- Galli, F., Nucci, S., Pirola, C., & Bianchi, C. L. 2014. Epoxy methyl soyate as bioplasticizer: Two different preparation strategies. *Chemical Engineering Transactions*.**37**: 601-606.
- GAMA. 2014. *Cellulose Acetate Polymer*. New York: Global Acetate Manufacturers Association.
- Gardner, H. A. & Sward, G. G. 1972. *Paint testing manual: Physical and chemical examination of paints, varnishes, lacquers, and colors*. American Society for Testing and Materials.
- Gettens, R. J. & Stout, G. L. 2012. *Painting materials: A short encyclopedia*. United States: Courier Corporation.
- Gribb, A. A. & Banfield, J. F. 1997. Particle Effects on Transformation Kinetics and Phase Stability in Nanocrystalline TiO₂. *American Mineralogist*. **82**: 717-728.
- Guo, Y. & Wu, P. 2008. Investigation of the Hydrogen-Bond Structure of Cellulose Diacetate by Two-Dimensional Infrared Correlation Spectroscopy. *Carbohydrate Polymers*. **74** (3): 509-513.
- Han, J. S. & Rowell, J. S. 1996. *Chemical Composition of Fibers. Paper and Composites from Agro-Based Resources*. Rowell, Young, and Rowell, eds., CRC Press Inc.
- Harkin, J. M. 1969. *Lignin and its Uses*. Forest Product Laboratory, Forest Service. U.S. Department of Agriculture.

- Hartman, J., Albertsson, A. C., & Sjöberg, J. 2006. Surface and bulk modified galactoglucomannan hemicellulose film and film laminates for versatile oxygen barriers. *Biomacromolecules*. **7** (6), 1983-1989.
- Haygreen, J.G. & Bowyer, J. L. 1989. *Forest Product and Wood Science*. 2nd ed. Iowa State University Press, United States.
- He, A., Liu, D., Tian, H., Jin, Y. Cheng, Q., & Song, J. 2014. Improving the Yield of Trimethylsilyl Cellulose by Activation of Cellulose with Ethylenediamine. *Cellulose Chemical Technology*. **48** (1-2): 19-23.
- Hegde, M., Palanisamy, K., & Jae, S. Y. 2013. Acacia mangium Willd.- A Fast Growing Tree for Tropical Plantation. *Journal of Forest Science*. **29** (1): 1-14.
- Hemmasi, A. H., Samariha, A., Tabei, A., Nemati, M., & Khakifirooz, A. 2011. Study of Morphological and Chemical Composition of Fibers from Iranian Sugarcane Bagasse. *American-Eurasian Journal of Agricultural and Environmental Science*.
- Hess, M., Hamburg, H. R., & Morgans, W. M. 1979. *Hess's Paint Film Defects: Their Causes and Cure*. New York: Halsted Press.
- Hicks, L. S. & Crewdson, M. J. 1995. Natural Weathering. In Koleske, J. V. 2012b. *Paint and coating testing manual*. ASTM International, pp. 619-642.
- Hillion, G., Delfort, B., le Penner, D., Bournay, L., & Chodorge, J. A. 2003. Biodiesel production by a continuous process using a heterogeneous catalyst. *Chemical Society, Division of Fuel Chemistry*. **48** (2): 636-638.
- Hirota, M., Furihata, K., Saito, T., Kawada, T., & Isogai, A. 2010. Glucose/Glucuronic Acid Alternating Co-polysaccharides Prepared from TEMPO-Oxidized Native Celluloses by Surface Peeling. *Angewandte Chemie International Edition*. **49** (42): 7670-7672.
- Horn, R. A. 1978. Morphology of Pulp Fiber from Hardwoods and Influence on Paper Strength. *Forest Product Laboratory: Research Paper FPL 312*. United States Department of Agriculture.
- Hubbert, M. K. 1956. Nuclear energy and the fossil fuels. *Drilling and Production Practice: American Petroleum Institute*.
- Humphries, M. 2009. *Fabric Reference*. 4th ed. USA: Prentice Hall.
- Hussain, M. A., Liebert, T. F., & Heinze, T. 2004. *Acylation of cellulose with n , n' -carbonyldiimidazole-activated acids in the novel solvent dimethyl sulfoxide/*

tetrabutylammonium fluoride. Macromolecular Rapid Communications. US: Wiley-VCH.

Indian Standard. 2002. *IS 5807 Part 6: Methods of Test for Clear Finishes for Wooden Furniture*. Painting, Varnishing, and Allied Finishes Sectional Committee. India: Indian Standards Institution.

Ioelovich, M. & Leykin, A. 2008. Structural investigations of various cotton fibers and cotton celluloses. *BioResources*. **3** (1): 170-177.

Ismail, J. & Ipor, B. 2004. Decay resistance of extractive-free Belian (*Eusideroxylon zwageri*) and Malagangai (*Protoxylon melagangai*). Proceedings of the *Conference on Forestry and Forest Products Research*: 308-315. Kuala Lumpur.

Jeon, B. Y., Kim, D. H., Na, B. K., Ahn, D. H., & Park, D. H. 2008. Production of Ethanol Directly from Potato Starch by Mixed Culture of *Saccharomyces cerevisiae* and *Aspergillus niger* using Electrochemical Bioreactor. *Journal of Microbiology and Biotechnology*. **18** (3): 545-551

Jonoobi, M. Harun, J., Shakeri, A., Misra, M., & Oksman, K. 2009. Chemical composition, crystallinity, and thermal degradation of bleached and unbleached kenaf bast (*Hibiscus cannabinus*) pulp and nanofibers. *Bioresources*. **4** (2): 626-639.

Kader, R. A. & Sahri, M. H. 1992. Processing and utilization of acacias, focusing on *A. mangium*. *Proceedings of Tropical Acacias in East Asia and the Pacific*. 86-91.

Kamide, K. 2005. *Cellulose and cellulose derivatives*. Netherlands: Elsevier.

Karatzos, S. K., Edye, L. A., & Wellard, R. M. 2012. The undesirable acetylation of cellulose by the acetate ion of 1-ethyl-3-methylimidazolium acetate. *Cellulose*. **19** (1): 307-312.

Kayserilioğlu, B. S., Bakir, U., Yilmaz, L., & Akkas, N. 2003. Use of xylan, an agricultural by-product, in wheat gluten based biodegradable films: mechanical, solubility and water vapor transfer rate properties. *BioResources*. **87** (3): 239-246.

Klemm, D., Philipp, B., Heinze, T., Heinze, U., & Wagenknecht, W. 1998. *Comprehensive Cellulose Chemistry: Functionalization of Cellulose*. US: Wiley-VCH.

- Koh, M. P. 2011. Chemical Composition. *In* Lim, S. C., Gan, K. S., & Tan, Y. E. (eds.). *Properties of Acacia mangium Planted in Peninsular Malaysia*. Forest Research Institute Malaysia, pp. 100-104.
- Koleske, J. V. 2006. Mechanical properties of solid coating. *Encyclopedia of Analytical Chemistry*.
- Koleske, J. V. 2012a. Mechanical Properties of Solid Coatings. *Encyclopedia of Analytical Chemistry*. United States: John Wiley and Sons.
- Koleske, J. V. 2012b. *Paint and coating testing manual*. ASTM International.
- Krässig, H. A. 1993. Cellulose, structure, accessibility and reactivity. Gordon and Breach Publishers, United States.
- Krishania, M., Kumar, V., Vijay, V. K., & Malik, A. 2013. Analysis of Different Techniques Used for Improvement of Biomethanation Process: A Review. *Fuel* 106.
- Krisnawati, H., Kallio, M., & Kanninen, M. 2011. *Acacia mangium Willd.: Ecology, Silviculture and Productivity*. Indonesia: Center for International Forestry Research.
- Kumar, P., Barrett, D. M., Delwiche, M. J., & Stroeve, P. 2009. Methods for Pretreatment of Lignocellulosic Biomass for Efficient Hydrolysis and Biofuel Production. *Industrial and Engineering Chemistry Research*. **48** (8): 3713-3729.
- Laidler, K. J. 1969. *Theories of Chemical Reaction Rates*. McGraw-Hill Publication.
- Laura L. Bunye. 1990. *Organosolv Pulping of Paraserianthes falcataria*. Malaysia: Universiti Putra Malaysia.
- Law, P. W., Longdon, A., & Willins, G. G. 2004. Solvent cast cellulose diacetate film. *Macromolecular symposia*. Wiley-VCH.
- Law, R. C. 2004. Cellulose acetate in textile application. *Macromolecular symposia*. Wiley-VCH.
- Lee Ann Goetz. 2012. *Preparation and Analysis of Crosslinked Lignocellulosic Fibers and Cellulose Nanowhiskers with Poly(Methyl-Vinyl Ether Co Maleic Acid) – Polyethylene Glycol to Create Novel Water Absorbing Materials*. United States: Georgia Institute of Technology.

- Lee, S. S. 2004. Disease and Potential Threats to *Acacia mangium* Plantations in Malaysia. *Unasylva* **217**. **55**: 31-35.
- Lemmens, R. H. M. J., Soerianegara, I. & Wong, W. C. 1995. Timber Trees: Minor Commercial Timbers. *Plant Resources of Southeast Asia*. **5** (2): 655.
- Li Jingjing. 2011. *Isolation of lignin from wood*. Finland: Saimaa University of Applied Sciences.
- Lim, S. C., Gan, K. S., & Choo, K. T. 2003. The Characteristics, Properties, and Uses of Plantation Timbers – Rubberwood and *Acacia mangium*. *Timber technology bulletin*. **26**: 1-11.
- Lim, S. C., Gan, K. S., & Tan Y. E. 2011. Properties of *Acacia mangium* planted in Peninsular Malaysia. *ITTO Project on improving utilization and value adding of plantation timbers from sustainable sources in Malaysia, Project No. PD 306/04(1)*.
- Limayem, A. & Ricke, S. C. 2012. Lignocellulosic biomass for bioethanol production: Current perspectives, potential issues and future prospects. *Progress in Energy and Combustion Science*. **38**: 449-467.
- Loo, M. M. L., Hashim, R., & Leh, C. P. 2012. Recycling of valueless paper dust to a low grade cellulose acetate: Effect of pretreatments on acetylation. *BioResources*. **7** (1): 1068-1083.
- Ma, X. M., Lu, R., & Miyakoshi, T. 2014. Application of pyrolysis gas chromatograph/ mass spectrometry in lacquer research: A review. *Polymers*. **6**: 132-144.
- Mari Granström. 2009. *Cellulose Derivatives: Synthesis, Properties and Applications*. Finland: University of Helsinki.
- Mesfun, S., Lundgren, J., Grip, C. E., Toffolo, A., & Rova, U. 2013. Techno-economic evaluation of butanol production via black liquor fractionation. *Proceedings of the 12th International Conference on Sustainable Energy Technologies*. Hong Kong.
- Morse, M. P. 2002. Flexibility and Toughness. In Koleske, J. V. (eds.). *Paint and coating testing manual*. ASTM International, pp 547-554.
- Müller, M. 2011. Influence of surface integrity on bonding process. *Research in Agricultural Engineering*. **57** (4): 153-162.

- Müller, M., Hrabě, P., Chotěborský, R., & Herák, D. 2006. Evaluation of Factors Influencing Adhesive Bond Strength. *Research in Agricultural Engineering*. **52** (1): 30-37.
- Muthu, H., SathyaSelvabala, V., Varathachary, T. K., KiruphaSelvaraj, D., Nandagopal, J., & Subramanian, S. 2010. Synthesis of biodiesel from neem oil using sulfated zirconia via transesterification. *Brazilian Journal of Chemical Engineering*. **27** (4): 601-608.
- Nag, A. 2008. *Biofuels Refining and Performance*. 1st ed. McGraw-Hill, United States.
- Narapakdeesakul, D., Sridach, W. & Wittaya, T. 2013. Synthesizing of oil palm empty fruit bunch lignin derivatives and potential use for production of linerboard coating. *Songklanakarin Journal of Science and Technology*. **35** (6): 705-713.
- Nascimento, M. S., Santana, A. L. B. D., Maranhao, C. A., Oliveira, L. S., & Bieber, L. 2013. Phenolic extractives and natural resistance of wood. *Biodegradation-Life of Science*. Intech Publishing.
- Neal, J. L. 1965. Factors Affecting the Solution Properties of Cellulose Acetate. *Journal of Applied Polymer Science*. **9** (3): 947-961.
- Orwa, C., Mutua, A., Kindt, R., Jamnadass, R., & Anthony S. 2009. Acacia mangium – Brown Salwood. *Agroforestry database: A tree reference and selection guide*.
- Palaypayon, C. M. & Batalon, J. M. 2002. Issues and facts on Yemane. *Research Information Series on Ecosystems*. **14** (3): 9-11.
- Pearson, G. P. & Moore, W. R. 1960. The Influence of Degree of Substitution on some Viscosity Parameters for Cellulose Nitrate. *International Journal for the Science and Technology of Polymers*. **1**: 144-150.
- PiiaValto. 2011. *Development of fast analysis methods for extractives in papermaking process waters*. Finland: University of Jyväskylä.
- Pinto, C. P., Evtuguin, D. V., & Neto, C. P. 2005. Chemical Composition and Structural Features of the Macromolecular Components of Plantation *Acacia mangium* Wood. *Journal of Agricultural and Food Chemistry*. **53** (20): 7856-7862.
- Prasad, V. & Weeks, E. R. 2009. Flow Fields in Soap Films: Relating Viscosity and Film Thickness. *The American Physical Society Review*. **80**: 026309.

- Pulkkinen, I., Fiskari, J., & Alopaeus, V. 2009. The Effect of Hardwood Fiber Morphology on the Hygroexpansivity of Paper. *Journal of Bioresources*. **4** (1): 126-141.
- Puls, J., Wilson, S. A., & Holter, D. 2011. Degradation of Cellulose Acetate-Based Materials: A Review. *Journal of Polymers and the Environment*. **19**: 152-165.
- Qiao, X., Wang, X., Zhao, X., Liu, J., & Mo, Z. 2000. Poly(3-dodecylthiophenes) Polymerizes with Different Amounts of Catalyst. *Synthetic Metals*. **114** (3): 261-265.
- Quiroz-Castaneda, R. E & Folch-Mallol, J. L. 2013. Hydrolysis of Biomass Mediated by Cellulases for the Production of Sugars. In Chandel, A. K. (eds.). *Sustainable degradation of lignocellulosic biomass – Techniques, applications, and commercialization*. Intech Open. Canada: Intech Publishing.
- Rahikainen, J. L., Martin-Sampedro, R., Heikkinen, H., Rovio, S., Marjamaa, K., Tamminen, T., Rojas, O. J., & Kruus, K. 2013. Inhibitory effect of lignin during cellulose bioconversion: The effect of lignin chemistry on non-productive enzyme adsorption. *BioResources*. **133**: 270-278.
- Rasheed, S., & Dasti, A. A. 2003. Quality and mechanical properties of plant commercial fibers. *Pakistan Journal of Biological Science*. **6** (9): 840-843.
- Rohula, U., Kawiji, E. N., Andre Y. T. P., & Andik S. 2013. The effect of cassava starch-based edible coating enriched with Kaempferia rotunda and Curcuma xanthorrhiza essential oil on refrigerated patin fillets quality. *International Food Research Journal*. **21** (1): 413-419.
- Royer, M., Rodriques, A. M. S., Herbette, G., Beauchêne, J., Chevalier, M., Hérault, B., Thibaut, B. & Stien, D. 2012. Efficacy of *Bagassaguianensis* Aubl. Extract Against Wood Decay and Human Pathogenic Fungi. *International Biodeterioration & Biodegradation*. **70**: 55-59.
- Rustemeyer, P. 2004. CA filter tow for cigarette filters. In Rustemeyer, P. Cellulose Acetates: Properties and Applications. *Macromolecular symposia*. **208** (1): 267-292. Weinheim: Wiley-VCH.
- Sabah Forest Industries. 2011. "Sabah Forest Industries (SFI) Sdn. Bhd.". Retrieved from <http://www.avanthagroup.com/downloads/Sabah-Forest-Industries-Sdn-Bhd.pdf>. 28 Dec. 2015.
- Sabah Forestry Department. 2012. Availability of Raw Material for Downstream Processing in Sabah. Paper presented at the Seminar on Sabah Furniture Industry- A Potential Hub for Outdoor Furniture. Suter Harbour, Sabah, Malaysia, 24 September.

- Sable, I., Grinfelds, U., Jansons, A., Vikele, L., Irbe, I., Verovkins, A., & Treimanis, A. 2012. Comparisons of the Properties of Wood and Pulp Fibers from Lodgepole Pine (*Pinus contorta*) and Scots Pine (*Pinus sylvestris*). *BioResources*. **7** (2): 1771-1783.
- SAFODA. Produk dari Acacia mangium. Retrieved from <http://ww2.sabah.gov.my/SAFODA/produk.html>. 27 Dec. 2015.
- Sahri, M. H., Ibrahim, F. H., & AbShukor, N. A. 1993. Anatomy of *Acacia mangium* grown in Malaysia. *IAWA Journal*. **14** (3): 245-251.
- Saka, S. 2004. Wood as natural raw materials for cellulose acetate production. In Rustemeyer, P. Cellulose Acetates: Properties and Applications. *Macromolecular symposia*. **208** (1): 7-28. Weinheim: Wiley-VCH.
- Samariha, A., Kiaei, M., Talaeipour, M., & Nemati, M. 2011. Anatomical Structure Differences Between Branch and Trunk in *Ailanthus altissima* Wood. *Indian Journal of Science and Technology*. **4** (12): 1676-1678.
- Sarmin, S. N., Zakaria, S. A. K. Y., Kasim, J. & Shafie, A. 2013. Influence of Resin Content and Density on Thickness Swelling of Three-layered Hybrid Particleboard Composed of Sawdust and *Acacia mangium*. *BioResources*. **8** (4): 4864-4872.
- Sata, H., Murayama, M., & Shimamoto, S. 2004. Properties and applications of cellulose triacetate film. *Macromolecular symposia*. Wiley-VCH.
- Savchenko, V. I. & Makaryan, I. A. 1999. Palladium Catalyst for the Production of Pure Margarine. *Platinum Metals Review*. **43** (2): 74-82.
- Schaller, C., Rogez, D., & Braig, A. 2008. Hydroxyphenyl-s-triazines: Advance Multipurpose UV-Absorbers for Coatings. *Journal of Coating Technology and Research*. **5** (1): 25-31.
- Shaikh, H. M., Pandare, K. V., Nair, G., & Varma, A. J. 2009. Utilization of Sugarcane Bagasse Cellulose for Producing Cellulose Acetates: Novel Use of Residual Hemicellulose as Plasticizer. *Carbohydrate Polymers*. **76** (1): 23-29.
- Shebani, A. N., van Reenen, A. J., & Meincken, M. 2008. The Effect of Wood Extractives on the Thermal Stability of Different Wood Species. *Thermochimica Acta*. **471** (1-2): 43-50.
- Sherbondy, V. D. 1995. Accelerated Weathering. In Koleske, J. V. 2012b. *Paint and coating testing manual*. ASTM International, pp. 643-653.

- Shokri, J. & Adibkia, K. 2013. Application of Cellulose and Cellulose Derivatives in Pharmaceutical Industries. *In* Ven, T. V. D. & Godbout, L. (eds.). *Cellulose - Medical, Pharmaceutical and Electronic Applications*. Intech Open. Intech Publishing, Canada.
- Siegel, R. W. 1992. Nanostructured materials. In Moran-Lopes, J. L. & Sanchez, J. M. (eds.). *Advanced topics in materials science and engineering*. New York: Plenum.
- Sinhsamouth Phouthavong. 1998. Growth performance and economic evaluation of *Acacia mangium* Willd. Planted at different spacings. Malaysia: Universiti Putra Malaysia.
- Sining Unchi. 1996. *Acetylation of Acacia mangium wood fibers and its application in the medium density fiberboard*. Malaysia: Universiti Putra Malaysia.
- Soo, M. C., Wan Rosli, W. D., & Leh, C. P. 2012. Improvement of Recycled Paper's Properties for the Production of Braille Paper by Impregnation with Low Grade Cellulose Acetate: Optimization Using Response Surface Methodology (RSM). *BioResources*. **7** (4): 5333-5345.
- Stefke, B., Windelsen, E., Schwanninger, M., & Hinterstoisser, B. 2008. Determination of the Weight Percentage Gain and of the Acetyl Group Content of the Acetylated Wood by Means of Different Infrared Spectroscopic Methods. *Analytical Chemistry*. **80** (4): 1272-1279.
- Steinmeyer, H. 2004. Chemistry of cellulose acetylation. *Macromolecular symposia*. Wiley-VCH.
- Stuart, B. 1997. *Biological Applications of Infrared Spectroscopy*. England: John Wiley and Sons.
- Summer Pacific. No yr. Our Products. Retrieved from <http://www.borneoforesthoney.com/products.php>. 27 Dec. 2015.
- Sun, Y., & Cheng, J. 2001. *Hydrolysis of Lignocellulosic Materials for Ethanol Production: A Review*. North Carolina: Elsevier.
- Swain, R. C., & Adams, P. 1940. Cellulose Acetate Coating Compositions. *U.S. Patent No. 2426379*: United States Patent Office.
- TAPPI T203 cm-09.2009. *Alpha-, Beta-, and Gamma-Cellulose in Pulp*. Atlanta, GA: TAPPI Press.
- TAPPI T204 cm-07. 2007. *Solvent Extractives of Wood and Pulp*. Atlanta, GA: TAPPI Press.

- TAPPI T222 om-11. 2011. *Acid-insoluble Lignin in Wood and Pulp*. Atlanta, GA: TAPPI Press.
- TAPPI T258 om-02. 2006. *Basic Density and Moisture Content of Pulpwood*. Atlanta, GA: TAPPI Press.
- TAPPI T9 m-54. 1998. *Holocellulose in Wood*. Atlanta, GA: TAPPI Press.
- Tejado, A., Pena, C., Labidi, J., Echeverria, J. J., & Mondragon, I. 2007. Physico-chemical characterization of lignins from different sources for use in phenol-formaldehyde resin synthesis. *BioResources*. **98** (8): 1655-1663.
- Tham, C. K. 1979. Trial of *Acacia mangium* Willd. as a Plantation Species in Sabah. *Forest Genetic Resources Information*. Food and Agriculture Organization (FAO).
- Togrul, H., & Arslan, N. 2004. Carboxymethyl Cellulose from Sugar Beet Pulp Cellulose as a Hydrophilic Polymer in Coating of Mandarin. *Journal of Food Engineering*. **62** (3): 271-279.
- Tomei, J., & Upham, P. 2009. Argentinean soy based biodiesel: An introduction to production and impacts. *Energy Policy*. **37** (10): 3890-3898.
- Towler, B. F. 2014. *The Future of Energy*. London: Academic Press.
- Tro, N. J. 2015. *Principles of Chemistry: A Molecular Approach*. USA: Pearson Education.
- Varmola, M. 2002. *Case Study of the Tropical Forest Plantations in Malaysia*. Forest Plantations Working Paper. Rome, Italy. June 2002. Organized by Food and Agriculture Organization of the United Nations.
- Varshney, V. K. & Naithani, S. 2011. Chemical Functionalization of Cellulose Derived from Nonconventional Sources. In Kalia, S., Kaith, B. S. & Kaur, I. (eds.). *Cellulose Fibers: Bio and Nano-Polymer Composites*, pp. 43-60. Springer-Verlag, Berlin Heidelberg.
- Villar, J. C., Revilla, E., Gomez, N., Carbajo, J. M., & Simon, J. L. 2009. Improving the use of kenaf for kraft pulping by using mixtures of bast and core fibers. *Industrial Crops and Products*. **29** (2-3): 301-307.
- Weizhen Zhu. 2013. *Equilibrium of lignin precipitation: The effects of pH, temperature, ion strength and wood origins*. Sweden: Chalmers University of Technology.

- Yamada, N., Khoo, K. C., & Mohd. Noor, M. Y. 1990. Sulphate Pulping Characteristics of *Acacia hybrid*, *Acacia mangium*, and *Acacia auriculiformis* from Sabah. *Journal of Tropical Forest Science*. **4** (3): 206-214.
- Yang, S. J., Bai, A. M., & Sun, J. T. 2006. Preparation of $\text{SO}_4^{2-}/\text{TiO}_2\text{-La}_2\text{O}_3$ solid superacid and its catalytic activities in acetalation and ketalation. *Journal of Zhejiang University Science*. **7** (7): 553-558.
- Zhang, S. Y., Wang, C. G., Fein B. H., Yu, Y., Cheng, H. T., & Tian, G. L. 2013. Mechanical function of lignin and hemicelluloses in wood cell wall revealed with microtension of single wood fiber. *BioResources*. **8** (2): 2376-2385.
- Zheng, Y., Pan, Z., & Zhang, R. 2009. Overview of biomass pretreatment for cellulosic ethanol production. *International Journal of Agriculture and Biological Engineering*. **2** (3): 51-68.
- Zhong, M. Q., Dai, H. H., Yao, H. F., Dai, D. X., Zhou, Y. G., Yang, J. T., & Chen, F. 2011. Strong, flexible high-lignin polypropylene blends. *Society of Plastics Engineer: Plastics Research Online*.
- Zhou, S., Yao, S., Xing, M., & Pu, J. 2010. Applied study of birch pulp bleaching using dimethyldioxirane to obtain acetate-grade pulp. *BioResources*. **5** (3): 1779-1788.
- Zorll, U. 2006. Adhesion Testing. In Tracton, A. A. (eds.). *Coatings Technology Handbook*. CRC Press: United States.
- Zugenmaier, P. 2006. Materials of Cellulose Derivatives and Fiber Re-inforced Cellulose-Polypropylene Composites: Characterization and Application. *Pure and Applied Chemistry*. **78** (10): 1843-1855.