

**PREPARATION AND CHARACTERIZATION OF TITANIUM (IV)-OXIDE  
IMMOBILIZED ON GRANULAR ACTIVATED CARBON**

***PREPARED BY:***

**MOH PAK YAN**

***PROJECT CODE:***

**B-09-01-01-ER/U130**

**PROGRAMME OF INDUSTRIAL CHEMISTRY  
SCHOOL OF SCIENCE AND TECHNOLOGY  
UNIVERSITI MALAYSIA SABAH**

**APRIL, 2007**



**UMS**  
UNIVERSITI MALAYSIA SABAH

## SYNOPSIS

Titanium (IV) oxide immobilized on granular activated carbon (as TiO<sub>2</sub>/GAC) was prepared through hydroxide precipitation of TiO<sub>2</sub> from titanium tetraisopropoxide followed by dip-coating and annealing at 550 °C. Photocatalytic activity of TiO<sub>2</sub>/GAC suspended in Methylene Blue (MB) aqueous solution had been investigated. It was found that the removal of MB by TiO<sub>2</sub>(0.010g)/GAC/UV system (i.e. 72%) had no significant difference compared to the summation of MB removal by TiO<sub>2</sub>(0.010g)/Pyrex/UV (i.e. 36%) and GAC/UV system (i.e. 42%) systems. However, comparison of the MB removal against the amount of TiO<sub>2</sub> shows that the removal was predominantly contributed by the TiO<sub>2</sub> that immobilized on the GAC. Furthermore, it was found that the activity of the TiO<sub>2</sub>/GAC/UV system had reached plateau when more than 0.022g of TiO<sub>2</sub> was immobilized on 0.5 g of GAC. In contrast, immobilization of 0.010g of TiO<sub>2</sub> on 0.5 g of GAC had present the highest photocatalytic activity where about 72% of the MB in the aqueous solution (with [MB] = 1 × 10<sup>-4</sup> molL<sup>-1</sup>) was removed. The pores on the GAC were believed to be able to adsorb the MB molecules and thus increasing the chances of MB degradation by the photoactivated TiO<sub>2</sub>. Its reaction kinetics was following the pseudo-first order rate law with the rate constant, *k*, is 0.0100 min<sup>-1</sup>. It implies that longer reaction time will give higher degree of removal where the MB molecule will continuously adsorb on the GAC then degraded by the photoactivated TiO<sub>2</sub>, and subsequently desorbed from the GAC.

# SINTESIS DAN PENCIRIAN TITANIUM (IV) OKSIDA YANG TERSALUT DI ATAS BUTIRAN KARBON TERAKTIF

## SINOPSIS

Titanium (IV) oksida yang tersalut di atas butiran karbon teraktif (sebagai TiO<sub>2</sub>/GAC) telah disediakan menerusi pemendakan hidroksida TiO<sub>2</sub> daripada titanium tetraisopropoksida diikuti dengan celup-angkat dan pemanasan berkala pada suhu 550 °C. Aktiviti pemangkinanfoto bagi ampaian TiO<sub>2</sub>/GAC dalam larutan akueus metilena biru (MB) telah dikaji. Didapati bahawa penyingkiran MB oleh sistem TiO<sub>2</sub>(0.010g)/GAC/UV (iaitu 72%) adalah tidak signifikan berbanding dengan hasil campur penyingkiran MB bagi sistem TiO<sub>2</sub>(0.010g)/Pyrex/UV (iaitu 36%) dan sistem GAC/UV (iaitu 42%). Walau bagaiman pun, perbandingan penyingkiran MB terhadap amaun TiO<sub>2</sub> menunjukkan bahawa penyingkiran MB yang utama adalah disumbangkan oleh TiO<sub>2</sub> yang tersalut di atas permukaan GAC. Tambahan pula, hasil kajian mendapati bahawa aktiviti sistem TiO<sub>2</sub>/GAC/UV akan menjadi tidak berkesan dan malar apabila berat TiO<sub>2</sub> yang melebihi 0.022g telah tersalut di atas 0.5 g GAC. Tambahan pula, penyalutan 0.010g TiO<sub>2</sub> di atas 0.5 g GAC telah menunjukkan aktiviti pemangkinanfoto yang tertinggi di mana 72% daripada MB dalam larutan akueus (dengan [MB] =  $1 \times 10^{-4}$  molL<sup>-1</sup>) telah disingkirkan. Dipercayai bahawa liang-liang pada GAC dapat menjerap molekul-molekul MB dan seterusnya meningkatkan peluang bagi TiO<sub>2</sub> yang teraktif-foto untuk menguraikan molekul MB tersebut. Kinetik tindak balasnya adalah mengikuti hukum kadar tertib pertama *pseudo* dengan pemalar kadar, *k*, bersamaan  $0.0100 \text{ min}^{-1}$ . Ia mengimplikasikan bahawa masa tindak balas yang lebih panjang akan memberikan darjah penyingkiran yang lebih tinggi di mana molekul-molekul MB akan terjerap pada GAC kemudian diurai oleh TiO<sub>2</sub> yang teraktif-foto, dan seterusnya ternyah-jerap dari GAC secara berterusan.